




SUNSORB LS-119

Chemical Name: 1,3,5-triazine-2,4,6-triamine,N,N''-[1,2-ethane-diyl-bis[[[4,6-bis-butyl(1,2,2,6,6-pentamethyl-4-piperidiny)amino]-1,3,5-triazine-2-yl]imino]-3,1-propanediyl]]-bis[N',N''-dibutyl-N',N''-bis(1,2,2,6,6-pentamethyl-4-piperidiny)]

Chemical Structure:

Molecular Weight: 2286

CAS NO: 106990-43-6

Specification:

Appearance: White to light yellow granule

Melting point: 115-150°C

Volatiles (10g/2hr/100°C): 1.0% max

Color of solution: 425 nm (10% w/v Toluene): 90.0% min
(Transmission) 450nm (10% w/v Toluene): 93.0% min
 500nm (10% w/v Toluene): 95.0% min

Ash: 0.1% max

Package: 20kgs Net/Carton inner with PE bag

50kgs Net/Carton inner with 2 PE bags

Application: Sunisorb LS-119 is particularly effective in polypropylene, polyethylene, α-olefin copolymers and blends with EPR, ERR, PE, EVA, EAA, EVOH and filled PP.