




SUNSORB LS-622

Chemical Name: Butanedioic acid, dimethylester, polymer with 4-hydroxy-2,2,6,6-tetramethyl-1-piperidine ethanol

Chemical Structure:



Molecular Weight: 3100-4000

CAS NO: 65447-77-0

Specification:

Appearance: White to light yellow crystalline powder

Melting range: 55-70°C

Loss on drying: 0.5% max

Color of solution (5g/100ml Toluene): 425nm 97.0% min

(Transmission) 450nm 99.0% min

Ash: 0.1% max

Package: 25kgs Net/Carton

Application: Main applications are Polyolefin (PP,PE), Olefin copolymers such as EVA as well as blends of Polypropylene with Elastomers.

It is also highly effective in Polyacetals, Polyamides and Polyurethane applications.